



HiChem Industries Pty Ltd.
73 Hallam South Road Hallam, Vic 3803
Phone (03) 9796 3400 Fax (03) 9796 4500
ACN 006-542-767



PRODUCT INFORMATION SHEET

z:\public\prodinfo\hardware\asu .doc 25-4-98

ACRYLIC SEALER UNDERCOAT

Description

HICHEM ACRYLIC SEALER UNDERCOAT is a quick drying water based sealer and undercoat for interior surfaces. Its formulation provides excellent hiding power and adhesion and is applied in an easy one coat application.

Uses

ACRYLIC SEALER UNDERCOAT is suitable for plaster, masonry, paperfaced wallboard and timber surfaces and can be used under water or oil based top coats.

Surface Preparation

Previously painted surfaces - Scape off loose and flaking paint and wash with sugar soap. Fill cracks and nail holes with suitable wood filler. Sand smooth and dust off. Sand Gloss and Semigloss surfaces thoroughly and wipe clean.

New surfaces - Brick, plaster, masonry, paperfaced wallboard and timber surfaces. Fill cracks and nail holes with a suitable filler. Sand smooth and dust off.

Thinning

ACRYLIC SEALER UNDERCOAT is supplied ready for use, however if surface is very porous or under hot conditions use 100ml of water per litre.

Application

Stir and mix contents thoroughly before use.

Apply one coat of *ACRYLIC SEALER UNDERCOAT* by brush or roller.

Drying time

Under normal conditions - touch dry in 20 minutes and can be recoated after 2 hours.

Coverage

Approx. 15 square metres per litre

Clean up

Use water.

Storage

Store in a cool dry place. Always replace the lid securely after use.

Safety

Provide adequate ventilation during use. See material safety data sheet.

Standard Packages and Product Codes

500 ml	ASU500
1 Litre	ASU1
4 Litre	ASU4

The information contained in this bulletin is presented in good faith based on thorough laboratory and field testing but without warranty. As we have no control over the conditions under which these products are used, it is recommended that all products be tested by the end user to ensure the suitability of the product for the particular application and conditions.