



HiChem Industries Pty Ltd.
73 Hallam South Road Hallam, Vic 3803
Phone (03) 9796 3400 Fax (03) 9796 4500
ACN 006-542-767



PRODUCT INFORMATION SHEET

z:\public\prodinfo\misc\bo .doc 25-4-98

BRUSH ON SOUND DEADENER

Description

MOTOSPRAY BRUSH ON SOUND DEADENER is a quick drying and flexible Underbody Protecting Schutz.

Uses

SOUND DEADENER provides sound deadening and protection against corrosion, dust, moisture, stone chips and abrasion. May be used under wheel arches, on underbody panels, insides of guards, quarter panels, and doors, floor pan and luggage compartments.

Properties

Colour - black
Flexible
Quick drying
Brushable

Thinning

If required, *SOUND DEADENER* can be thinned with *ENAMEL THINNER* or *MINERAL TURPS*.

Surface Preparation

Remove all surface dirt with a wire brush, and wipe over with *PREPWASH* ensuring that surface is clean, dry and dust free.

Substrates

Bare Metal.: For maximum long term protection bare metal should be primed with EPS or Superetch primer.
Existing paintwork in good condition.

Application

1. STIR WELL.
2. Apply 1-3 coats with stiff bristled brush. Allow a flash off time of 15 minutes between coats. Do not coat functional parts such as springs, exhausts, drive shafts, wheels etc.

Drying Time

Finish will be touch dry in 20 minutes and will set hard in 1 to 4 hours depending on air temperature.

Clean up

Clean up using *MINERAL TURPS*.

Storage

Store in a cool dry place. Always replace the lid securely after use.

Safety

See material safety data sheet.

Standard Packages and Product Codes

1 litre	BO1
4 litre	BO4
20 litre	BO20

The information contained in this bulletin is presented in good faith based on thorough laboratory and field testing but without warranty. As we have no control over the conditions under which these products are used, it is recommended that all products be tested by the end user to ensure the suitability of the product for the particular application and conditions.