




HiChem Paint Technologies Pty Ltd.
73 Hallam South Road Hallam, Vic 3803
Phone (03) 9796 3400 Fax (03) 9796 4500
ABN 95 064 139 653



PRODUCT INFORMATION SHEET

24-10-11

PAVING PAINT

Description

HiChem Paving Paint is a synthetic enamel based on high performance alkyd resins. *Paving Paint* offers high gloss with outstanding flow properties.

Uses

For coating concrete floors.

Properties

Outstanding gloss
Excellent flow properties
Tough, durable finish

Surface preparation

Ensure surface is clean and dry.

Thinning

Thin with up to-20% *Mineral Turps*.

Application

Apply by brush or roller (short nap).
Recommended Dry Film Thickness is 40 microns. Do not exceed 75 microns total Dry Film Thickness.

Recoat: If additional coats are required, allow a minimum of 48 hours before applying Paving Paint otherwise wrinkling or a delayed curing may occur.

DO NOT FORCE DRY.

In hot weather care should be taken to avoid the application of heavy coats as wrinkling may result.
Finished work should not be allowed to dry in the sun.

Cleanup

Use *Mineral Turps* or *Superglow Multipurpose Thinner*.

Drying Time

At 20°C and dry film build 40 microns.
Dust free – 45 minutes.
Tack free - 1 hour.
Hard dry - 16 hours.
Full cure - enamels continue to harden up to 4 weeks depending on temperature and film thickness.
A period of 4 weeks should be allowed before using detergent or polishing wax.
Do not allow contact with water for a period of 5 days.

Storage

Store in a cool dry place. Always replace the lid securely after use.

Safety

See material safety data sheet

Coverage

Approx. 9 square meters per litre at 40 micron dry film thickness.

The information contained in this bulletin is presented in good faith based on thorough laboratory and field testing but with out warranty. As we have no control over the conditions under which these products are used, it is recommended that all products be tested by the end user to ensure the suitability of the product for the particular application and conditions.