



HiChem Industries Pty Ltd.
73 Hallam South Road Hallam, Vic 3803
Phone (03) 9796 3400 Fax (03) 9796 4500
ACN 006-542-767



PRODUCT INFORMATION SHEET

G:\SECURE\Product Information\MISC\SO.DOC 25/09/01

SPRAY ON SOUND DEADENER

Description

MOTOSPRAY SPRAY ON SOUND DEADENER is a quick drying, textured and flexible underbody protecting schutz.

Uses

SOUND DEADENER provides sound deadening and protection against corrosion, dust, moisture, stone chips and abrasion. May be used under wheel arches, on underbody panels, insides of guards, quarter panels and doors; also floor pans and luggage compartments.

Properties

Colour - black
Textured finish
Flexible
Quick drying

Thinning

If required, *SOUND DEADENER* can be thinned with *ENAMEL THINNER E250* or *MINERAL TURPS*.

Surface Preparation

Remove all surface dirt with a wire brush, and wipe over with *PREPWASH* ensuring that surface is clean, dry and dust free.

Remove any rust by grinding off or sanding then treat the area with *RUST REMOVER GEL*. Alternatively treat rust with *MOTOSPRAY RUST CONVERTER AND PRIMER SEALER*.

Suitable Substrates

1. Bare metal (properly prepared). But for maximum long term protection bare metal should be primed with *ENAMEL PRIMER SURFACER*, *SANDABLE PRIMER (Aerosol)* or *SUPERETCH PRIMER*.
2. Existing paintwork in good condition.

Application

1. STIR WELL.
2. Wipe all surfaces clean with *PREPWASH*.
3. For SO1 AND SO1.15 screw can onto the special wide bore schutz gun and spray at pressures from 345 kPa to 690 kPa depending on flow rate required. Pressure may be varied to obtain the desired textured effect. Do not coat functional parts such as springs, exhausts, drive shafts, etc. Apply 2-3 coats allowing 5-10 minutes flash off time between coats.
4. For aerosol SO400 spray several light coats.

Drying Time

Finish will be touch dry in 20 minutes and will set hard in 1 to 4 hours depending on air temperature and film thickness.

Coverage

Approximately 5 square metres per litre at a dry film thickness of 100 micron.

Clean up

Clean up using *MINERAL TURPS* or *ENAMEL THINNER E250*.

Storage

Store in a cool dry place. Always replace the lid securely after use.

Safety

See material safety data sheet.

Standard Packages and Product Codes

400g aerosol	SO400
1 litre	SO1
1.15 litre	SO1.15
4 litre	SO4
20ltr	SO20

The information contained in this bulletin is presented in good faith based on thorough laboratory and field testing but without warranty. As we have no control over the conditions under which these products are used, it is recommended that all products be tested by the end user to ensure the suitability of the product for the particular application and conditions.